



338 REMINGTON ROAD
CUYAHOGA FALLS, OH 44224
Phone: 330.920.3125 Fax: 330.920.3126

SS-5061

Product Description

SS-5061 is a RT curing silicone gel developed for applications requiring a low specific gravity silicone product. SS-5061 is a 2-part, 1:1 mix ratio silicone. Room temperature mixing of SS-5061 results in a cure time of 1 hour. SS-5061 can also be heat cured at 150°C to yield a cure time of less than 15 minutes. When cured, the elastomer resists weathering, ozone, moisture, UV and high temperatures.

Product Features

- Excellent moldability and conformation to plastic, metal and glass parts
- Convenient 1:1 mix ratio

Typical Applications

- Electronic component vibration, shock and thermal insulation
- Potting and encapsulation
- Dust and moisture protection
- Dielectric and insulation

Chemical Cure System

Platinum catalyzed, addition cure



Low Specific Gravity Encapsulant Gel

Typical Properties

Color	Light Blue
Viscosity, cps	1,000
Specific Gravity	0.76
Consistency	Light liquid
Work Time @ RT	30 Minutes
Cured @ RT	60 Minutes
Cured @ 150°C	15 Minutes
Dielectric Strength	>10 KV/mm
Dielectric Constant	2.8
Dissipation Factor	0.001
Volume Resistivity	1.0 x 10 ¹⁵
Coefficient of Thermal Expansion	1.0 x 10 ⁻³

Handling Precautions

This is a platinum cure system product. The catalyst can be deactivated by exposure to sulfur containing compounds like thiols, sulfides, sulfates, organic rubber containing sulfur, nitrogen containing compounds like amines, amides, imides, azides, tin metals or compounds, or tin cured RTV's.

Solids

99% solids

Limitations

Allow to fully cure before putting assembly into service. Ensure enough product remains between flanges to be effective in an assembly.

Adhesion

This product offers minimal adhesion to plastics, metals and typical substrates

Handling and Safety

For maximum shelf life, keep containers sealed when not in use. Keep out of the reach of children. Uncured sealant irritates eyes and skin. Refer to the SDS.

Shelf Life

Sealed containers are guaranteed for 12 months from the ship date when stored in a cool dry area below 70°F.

Applicable Standards

Conforms to GM low volatility requirements.

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as warranty, either expressed or applied. User shall rely on his/her own information and tests to determine suitability of the product for the intended use, and the user assumes all risk and liability resulting from the use of this product. Manufacturer's sole responsibility shall be to replace that portion of product that the manufacturer proves to be defective. Manufacturer shall not be liable to the buyer or any third party for injury, loss or damage directly or indirectly resulting from the use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding by the manufacturer.

This product has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses which implantation within the human body is intended.

*******Customized versions available upon request*******