



338 REMINGTON ROAD
CUYAHOGA FALLS, OH 44224
Phone: 330.920.3125 Fax: 330.920.3126

SS-24

Product Description

SS-24 is an electrically conductive, moisture curing silicone RTV. SS-24 is a 1-part silicone that when applied to the substrate, it is flexible and allows handling of the assembly within an hour. SS-24 works well in manual and automatic dispensing equipment.

Product Features

- Fast RT Cure
- Thixotropic Paste
- High Temperature Resistant
- Non-Corrosive

Typical Applications

- Form In Place Gaskets
- Electrically Conductive Shielding
- EMI/RFI Silicone Shielding

Chemical Cure System

Oxime



Electrically Conductive Silicone RTV

Typical Properties

Color	Dark Gray
Viscosity, cps	500,000
Specific Gravity	2.09
Consistency	Thixotropic Paste
Working Time @ RT	15 Minutes
Tack Free Time @ RT	60 Minutes
Application Rate, 90 PSI g/min	400
Cure Time	72 Hours @ RT
Durometer	60 Shore A
Tensile Strength	300 PSI
Volume Resistivity	0.09 Ohms-cm
Thermal Conductivity	2.5 W/m/K
Conductive Filler	Nickel Graphite

Curing

Cure speed can be accelerated with increased humidity and heat to very rapid cure times. Typical utilization involves dispensing in open air and after exposure to ambient humidity, a room temperature cured rubber with electrically conductive properties is formed.

Solids

98% solids

Adhesion

Primerless adhesion to most metals and typical substrates

Service Temperature

-45 to 260°C

Limitations

Allow to fully cure before putting assembly into service. Ensure enough product remains between flanges to be effective in an assembly.

Handling and Safety

For maximum shelf life, keep containers sealed when not in use. Keep out of the reach of children. Uncured sealant irritates eyes and skin. Refer to the SDS.

Shelf Life

Sealed containers are guaranteed for 12 months from the ship date when stored in a cool dry area below 70°F.

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as warranty, either expressed or applied. User shall rely on his/her own information and tests to determine suitability of the product for the intended use, and the user assumes all risk and liability resulting from the use of this product. Manufacturer's sole responsibility shall be to replace that portion of product that the manufacturer proves to be defective. Manufacturer shall not be liable to the buyer or any third party for injury, loss or damage directly or indirectly resulting from the use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding by the manufacturer.

This product has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses which implantation within the human body is intended.

*******Customized versions available upon request*******